



Description

LABPOX MVB FAST is a 100% solids two-component moisture vapor barrier epoxy coating with virtually no VOCs. LABPOX MVB FAST acts as a moisture barrier for concrete floors with high residual humidity (up to 100%) as well as new concrete slabs installed within 28 days. LABPOX MVB FAST is used as a primer prior installing a complete epoxy or polyaspartic system. The product can receive a subsequent layer of coating in as little as three hours, thus enabling very rapid commissioning. The product has been formulated with state-of-the-art components and one of the most efficient vapor barrier systems in the industry.

Uses

The LABPOX MVB FAST provides excellent results for the most demanding applications:

- + Industrial, commercial and residential uses
- + Manufacturing facilities
- + Warehouses
- + Commercial centers
- + Office buildings
- + Retail stores
- + Garages
- + Food/beverage processing and preparation plants
- + Public facilities including hospitals and schools
- + Pharmaceutical companies

Advantages

- + Environment friendly (100% solids, VOC-free and no solvent)
- + Virtually odor free
- + Quick curing
- + Suitable for damp concrete substrates
- + Effective membrane against residual moisture up to 100%
- + High degree of permeability
- + Ideal for concrete slabs with less than 28 days of curing
- + Potential for LEED eligibility
- + Can be used in combination with epoxy or polyaspartic floor systems
- + Low viscosity, easy to apply
- + Indoor and outdoor use

Application Data

Mix Ratio	2.4A:1B
Packaging	2.5 US Gal Kit 1 x 6.67 L (A) + 1 x 2.78 L (B)
Color	Clear, Grey, Tan, Black, White

Solids Coverage / US GAL	Mils	Sq. Ft.
	10	160
	12	133
	14	114
Recommended	16	100
	18	89
	20	80

Shelf Life	One year, in original unopened factory pails under normal storage conditions
-------------------	--

Pot Life	20 min
-----------------	--------

Application Temperature	Min 16°C / 61°F, Max 30°C / 86°F
--------------------------------	----------------------------------

Cure Time	22°C / 72°F and 50% Rel. Hum.
Working time	20 min
Tack Free	3 h
Recoat	3 - 24 h
Dry Through	14 h
Foot Traffic	24 h
Full Cure	1 week

Technical Properties

Hardness ASTM D2240	80	Shore D at maturity
Solids Content	100%	
Viscosity (A&B)	1050 +/-50 cps	
VOC Content	0 g/l	
Permeability (dry concrete) ASTM E96	< 0.1 perms @ 10 mils	
Permeability (up to 100% residual humidity) ASTM E96	< 0.1 perms @ 16 mils	

Surface Preparation

Concrete should be clean, dry and free of grease, oil, paint, curing agents or any contaminants that may inhibit proper adhesion. The surface humidity should be controlled for more than three hours prior installing the LABPOX MVB FAST.

Proper testing procedures should be practiced with regards to soil acidity and moisture vapor transmission. Take a pH reading to ensure concrete is neutral (a reading between 5 and 9 is acceptable). Use a Tramex® CME / CMExpert to measure the moisture content of the concrete slab. The first thing to do is to make sure that the floor is completely dry before application. Floors with higher results can receive the LABPOX MVB moisture mitigation.



Surface must be shot blasted or prepared with an equivalent mechanical means in line with CSP-2 or more depending on the application. Ensure the surface is free of contaminants, and the pores are open to allow the product to penetrate.

When installing a broadcast decorative system, after appropriate hardness has been reached, the base coat in which the aggregates are broadcasted should be carefully scraped and swept and then thoroughly vacuum cleaned to remove any remaining residues prior applying the topcoat. Contact us for more details on how to use the product with broadcast systems.

Mixing

Before final mixing, pre-mix part A at low speed using a Jiffy® or an Exomixer® mixer blade. Special attention must be paid to colored versions of the product since pigments may have separated from the rest of the formulation during storage. Mixing should be done until the color is uniform. If a metal pigment system is being considered, it is imperative to read the LABTEC Metallic Pigments data sheet for mixing times as well as application advice.

Then, using a Jiffy® or an Exomixer® mixer blade, mix two parts of A and one part of B together at low speed in a separate container. The mixing container must be clean and free of any outside particles. Mix thoroughly for a minimum of three minutes, until a completely homogeneous mixture is obtained. Use a low-speed drill (300-450 rpm) to minimize the air entrapment. It is recommended to activate the mixer in the reverse mode after the first 90 seconds for the liquid to mix from the bottom of the mixing can to the top. Make sure to scrape sides and bottom of mixing container so no unmixed material remains. Mix only the necessary quantity to be used according to the specified pot life / working time. Once the product is properly mixed, it needs to be immediately poured on the floor. Leaving mixed material for too long in a mixing pail will create an exothermic reaction and the product will no longer be usable.

Application

The LABPOX MVB FAST has been specifically designed to adhere to damp concrete substrates with a residual humidity of up to 100% and new concrete slabs having been installed within 28 days. Note that very high levels of humidity may also indicate a hydrostatic pressure problem. Hydrostatic pressure is usually caused by a drainage failure or a water leak. Make sure the causes of hydrostatic pressure are checked before installing the product.

Apply only when air and floor temperature is between 16°C / 61°F - 30°C / 86°F, and with a relative humidity of less than 85%. If a heated floor is installed, ensure that the system is turned off 2-4 hours (depending on type of radiant floor) before application

and for the full duration of the cure. The product has been specifically designed to adhere to concrete surfaces. Make sure the concrete surface is completely dry at the time of installation. The surface humidity must be controlled for more than three hours, which corresponds to the time required for the product to harden sufficiently.

If floor repairs are to be made, use cementitious repair products which can dry adequately in the presence of moisture or use LABPOX MVB FAST mixed with silica or other filling agents. When mixed with silica or other filling agents, use a low-speed drill to minimize the entrapment of air.

The vapor barrier performance of the product is directly proportional to the thickness of the coating. Labsurface recommends 16 to 18 mils. The vapor barrier protection increases with thickness. It is also important that the film thickness is uniform over the entire floor.

Rapid Aggregates System with Vinyl Flakes or Anti-Slip Finish

When the surface has been properly prepared, apply 16-18 mils of the LABPOX MVB FAST using a squeegee and back roll to even out the surface. It is recommended to apply the product in a multidirectional manner (north-south, east-west) to ensure that the desired coverage rate is achieved. Saturate to rejection with 1) vinyl flakes and install a polyaspartic or epoxy topcoat or 2) silica sand for an anti-slip system. For increased and more consistent permeability over the entire covered area when silica sand is used, install two coats of 8-9 mils each and saturate only the second coat with aggregates. Then, scrape or broom sweep and vacuum the surface to remove all loose particles before continuing with a LABFAST, LABSHIELD or LABPOX system.

System with Optimal Permeability

For a system with optimal permeability and to achieve the specified level of permeability less than or equal to 0.1 perm according to ASTM E96, the following steps need to be completed. First use the clear version of the LABPOX MVB FAST for optimal adhesion and permeability. When the surface has been properly prepared, apply the first coat at 6-8 mils with a squeegee (no back roll) to allow a good seal of the surface and to minimize the pinholes phenomenon. Once dry, if there are pinholes, scrape to burst bubbles and clean. Then repair the pinholes using the LABPOX MVB FAST mixed with silica sand. While mixing the silica sand, make sure there is no air bubbles trapped in the mix. Then spread the second coat of LABPOX MVB FAST to a minimum thickness of 8-10 mils (for a total system thickness of 16 mils or more) using a squeegee and back roll to even out the surface. It is recommended to apply the product in a multidirectional manner (north-south, east-west) to ensure that the desired coverage rate is achieved. Then, continue building the system with a LABPOX 30, 40 UV or 35 epoxy. A polyaspartic



system can only be considered following the installation of a layer of LABPOX 30, 40 UV and 35 for proper adhesion. Any repairs before or during the application of the system should be made with the LABPOX MVB FAST. No repair with CRACK FILLER or INSTANT PU REPAIR is recommended as it will affect the permeability of the system.

Recoat

Do not recoat without sanding if last coating of the product has been applied for more than 24 hours. The floor surface should be sanded/abraded until a uniform dullness is achieved. There should be no gloss on the prior coating after vacuuming and before applying the next coat. No need to sand if silica broadcast technique to saturation was used.

LABPOX products chemically adhere to LABPOX MVB FAST without sanding within a 24-hour window. LABFAST and LABSHIELD systems do not chemically adhere to LABPOX MVB FAST and adhesion is suboptimal even when the product is sanded. For LABFAST and LABSHIELD systems, it is therefore necessary to use aggregates (flakes or silica sand in full saturation) in order to obtain good adhesion. Contact LABSURFACE to obtain more details on systems including our recommendations if an external system is envisaged.

Limitations

The surface humidity must be controlled for more than three hours, the time required for the product to harden sufficiently. If this applies, make sure that the causes of hydrostatic pressure are checked before installing the product. The LABTEC Universal Pigment Pods are not compatible with the LABPOX MVB FAST. Although this product may be applied in a wide range of thickness, limitations may apply when taking into consideration curing time. Everything else being equal, thicker is the film, quicker is the curing time. Temperature will also impact curing time. Curing time may extend significantly at low temperature levels and the surface may be affected. Leaving mixed material for too long in a mixing pail will create an exothermic reaction and the product will no longer be usable. Do not clean the finished surface during the week following installation. Keep the product stored at room temperature to ensure consistent results.

Labsurface stands behind the quality of its products. However, Labsurface cannot guarantee results since Labsurface has no control over surface preparation, operating conditions and application procedures. Clients are solely responsible to test Labsurface's products to determine if they perform as expected. Although Labsurface makes reasonable efforts to control the quality of the finished product and its components, ASTM results may vary depending on the quality of the inputs delivered to Labsurface.

To meet our strict requirements, we are continuously testing our coatings and on occasion, formulations may be modified to improve certain properties within each coating. Information and data included in this reference document may not be up to date as of the date of reference. Contact Labsurface for further information regarding the limitations of this product.

Exposure to certain chemicals may cause reactions similar to those experienced with allergies. Chemicals that may cause sensitivity include synthetic and natural substances found in the Part A or the Part B of flooring or casting products. Once cross linked and completely cured, those substances are inert and therefore should not result in allergic reactions. Raw materials used by Labsurface do not differ significantly from comparable products manufactured by our competitors.

Refer to the most recent Material Safety Data Sheet prior using this product.

Available Colors

Clear, Grey, Tan, Black, White

Not compatible with LABTEC Universal Pigment Pods

Labsurface

101-1079 des Forges, Terrebonne, QC, Canada J6Y 0J9
Phone: 450-966-9000 / Fax : 450-621-3135
Labsurface.com